

Abstract

- 5 Gold oxide is precipitated together with iron oxide from a solution containing a gold source and an iron source; the gel formed thereby is washed, dried, ground to a size range of 0.85mm to 4.25mm and calcined; then used as a catalyst for oxidizing CO to CO₂ in the presence of a large excess of hydrogen.